

AD-A694 987

AERONAUTICAL RESEARCH LABS MELBOURNE (AUSTRALIA)

F/S 11/6

NITRIDING OF CHROMIUM IN NITROGEN GAS AT HIGH TEMPERATURE. (U)

OCT 79 T HILLS

UNCLASSIFIED

ARL/MAT/NOTE-128

NL

1 of 1  
084987

END  
DATE  
FILMED  
3-89  
DTIC



**DEPARTMENT OF DEFENCE**  
**DEFENCE SCIENCE AND TECHNOLOGY ORGANISATION**  
**AERONAUTICAL RESEARCH LABORATORIES**

MELBOURNE, VICTORIA

MATERIALS NOTE 128

THE AERONAUTICAL RESEARCH LABORATORIES  
TECHNICAL REPORT NO. 128  
MELBOURNE, VICTORIA  
1979

**NITRIDING OF CHROMIUM IN NITROGEN GAS**  
**AT HIGH TEMPERATURE**

by

T. MILLS

Approved for Public Release.



© COMMONWEALTH OF AUSTRALIA 1979

COPY No 20

OCTOBER 1979

81 2 13 021

AD A094987

DDC FILE COPY

DEPARTMENT OF DEFENCE  
DEFENCE SCIENCE AND TECHNOLOGY ORGANISATION  
AERONAUTICAL RESEARCH LABORATORIES

## MATERIALS NOTE 128

**NITRIDING OF CHROMIUM IN NITROGEN GAS  
AT HIGH TEMPERATURE,**

by

T. MILLS

## SUMMARY

Parabolic rate constants of the reaction of chromium with nitrogen gas under oxygen-free conditions have been determined over a range of temperature (1000–1250°C) and nitrogen pressure (0.265–101.33 kPa). The growth rate of the subnitride was measured by a thermogravimetric technique using a single specimen. Wagner's oxidation theory is used to calculate the self-diffusivity and intrinsic diffusivity of nitrogen in the subnitride from a theoretical analysis of the parabolic rate constant. The calculated diffusivities varied with the composition of the subnitride, having minimum values at intermediate compositions of the non-stoichiometric chromium nitride,  $\text{Cr}_2\text{N}$ .

## DOCUMENT CONTROL DATA SHEET

Security classification of this page: Unclassified

1. Document Numbers (a) AR Number: AR 001 802 (b) Document Series and Number: Materials Note 128 (c) Report Number: ARL Mat Note 128	2. Security Classification (a) Complete document: Unclassified (b) Title in isolation: Unclassified (c) Summary in isolation: Unclassified													
3. Title: NITRIDING OF CHROMIUM IN NITROGEN GAS AT HIGH TEMPERATURE														
4. Personal Author(s): T. Mills	5. Document Date: October 1979													
6. Type of Report and Period Covered:														
7. Corporate Author(s): Aeronautical Research Laboratories	8. Reference Numbers (a) Task: DSI 76 93 (b) Sponsoring Agency:													
9. Cost Code: 35 4745														
10. Imprint (Publishing establishment): Aeronautical Research Laboratories, Melbourne	11. Computer Program(s) (Title(s) and language(s))													
12. Release Limitations (of the document) Approved for Public Release														
12-0 Overseas: <table border="1"> <tr> <td>N.O.</td> <td></td> <td>P.R.</td> <td>I</td> <td>A</td> <td></td> <td>B</td> <td></td> <td>C</td> <td></td> <td>D</td> <td></td> <td>E</td> </tr> </table>		N.O.		P.R.	I	A		B		C		D		E
N.O.		P.R.	I	A		B		C		D		E		
13. Announcement Limitations (of the information on this page): No Limitation														
14. Descriptors: Chromium Chromium alloys Nitriding Nitrogen	15. Cosalt Codes: 1106 2012 Pressure Kinetics Mechanical properties Diffusivity													

## 16. ABSTRACT

*Parabolic rate constants of the reaction of chromium with nitrogen gas under oxygen-free conditions have been determined over a range of temperature (1000–1250 °C) and nitrogen pressure (0.265–101.33 kPa). The growth rate of the subnitride was measured by a thermogravimetric technique using a single specimen. Wagner's oxidation theory is used to calculate the self-diffusivity and intrinsic diffusivity of nitrogen in the subnitride from a theoretical analysis of the parabolic rate constant. The calculated diffusivities varied with the composition of the subnitride, having minimum values at intermediate compositions of the non-stoichiometric chromium nitride  $\text{Cr}_3\text{N}_2$ .*

## CONTENTS

	Page No.
1. INTRODUCTION	1
2. EXPERIMENTAL	1
3. RESULTS	1
4. DISCUSSION	2
5. CONCLUSIONS	3
TABLE	
REFERENCES	
FIGURES 1 6	
DISTRIBUTION	

A

## 1. INTRODUCTION

The mechanical properties of chromium and chromium-base alloys are adversely affected by their reaction with nitrogen at high temperatures and a knowledge of nitriding kinetics is expected to be helpful in the development of chromium-base alloys for gas turbine applications. Although the rate of nitriding of chromium has been studied by several investigators,<sup>1-4</sup> the data are very limited: only Schwerdtfeger<sup>1</sup> studied the effect of nitrogen pressure and his study was restricted to two temperatures, 1100° and 1200°C. The subnitride "Cr<sub>3</sub>N" film formed on chromium is uniform in thickness, dense and adherent, and its formation follows parabolic kinetics. It has been clearly established<sup>1,3,4</sup> that the growth of the film occurs by the diffusion of nitrogen through the nitride film.

The present work was undertaken to study the kinetics of the growth of chromium subnitride on chromium in nitrogen gas over the temperature range 1000°-1250°C as a function of nitrogen pressure, and to analyse the kinetic data using the detailed equilibrium measurements on the Cr-N system previously reported by the present author.<sup>5,6</sup>

## 2. EXPERIMENTAL

A gravimetric technique was used to determine the rate of nitriding. The thermobalance was a Cahn automatic recording R.G. Electrobalance and the apparatus for temperature control, pressure control and nitrogen purification has been described in detail elsewhere.<sup>7</sup> The important feature of the system is the use of a 150 mm tube of nitrided titanium at the bottom of the alumina reaction tube. The specimen was suspended in the centre of this tube, which eliminated the possibility of oxidation of the specimen by residual oxygen and water vapour in the apparatus.

Only one specimen, with dimensions 8 × 8 × 2.4 mm, was used in the experiments. It was prepared from rolled strip of high-purity electrolytic chromium by polishing with abrasive papers under kerosene down to 40, then washing (in turn) in petroleum ether, alcohol and acetone. The specimen was de-oxidized in the apparatus in hydrogen at 1200°C for 3 hours prior to the nitriding studies. Before each test, the specimen was equilibrated at the test temperature in nitrogen at a pressure just below the dissociation pressure of "Cr<sub>3</sub>N". The pressure was then raised to the value selected for the test. At the end of a test, the pressure was reduced so that the "Cr<sub>3</sub>N" dissociated and the chromium specimen was regenerated for the next test. With this procedure, the measurements were made in a very short time and the uncertainties associated with the use of separate specimens for each test were eliminated.

## 3. RESULTS

It was found, in agreement with the results of other workers, that the nitriding of chromium follows the parabolic law

$$\left( \frac{\Delta W}{A} \right)^2 = k_p t \quad (1)$$

where  $\Delta W$  = weight change during nitriding,  $A$  = surface area of the specimen,  $k_p$  = parabolic rate constant, and  $t$  = reaction time. Figures 1 and 2 show typical results in accordance with this law. Dependence of  $k_p$ , Table I, on nitrogen pressure and temperature is shown in Figure 3 where  $k_p$  is plotted against  $\log p_{N_2}$ . For clarity and compactness, the values of  $k_p$  are scaled by a factor B and displaced by a constant C (shown on figure). The relation between  $k_p$  and  $\log p_{N_2}$  is best represented by a sigmoidal-shaped curve. The inflection is more evident at the

lower temperatures, where, with nitrogen pressures restricted to 1 atmosphere, it was possible to study the reaction with compositions at the subnitride/nitrogen interface close to the upper limiting composition of "Cr<sub>2</sub>N". Above 1100°C, much higher pressures are required to study the same composition range e.g. at 1250°C, the "Cr<sub>2</sub>N"/CrN equilibrium pressure is about 1160 kPa<sup>5</sup>.

Schwerdtfeger's<sup>1</sup> results are also plotted in Figure 3. At 1200°C, at the high pressure end, his values for  $k''$  are lower than the present results. At 1100°C, Schwerdtfeger ignored one value of  $k''$  and his curve showed no inflection. If equal weight is attached to each point, agreement with the present work at 1100°C is very good and a sigmoidal-shaped curve is obtained.

#### 4. DISCUSSION

Wagner<sup>7</sup> derived an expression relating the parabolic rate constant and the diffusion coefficients of the anions and cations in the scale formed on a metal through reaction with a gas. In the case of "Cr<sub>2</sub>N", where nitrogen is the diffusing species, Wagner's equation gives the following relation between  $k''$  and the self-diffusivity of nitrogen  $D_N^*$ .

$$k'' = \int_{a_{N_i}}^{a_{N_s}} \frac{a_{N_s}}{2c^2 D_N^*} d \ln a_N \quad (2)$$

where  $k''$  is in [(g nitrogen)<sup>2</sup> m<sup>-1</sup> min<sup>-1</sup>],  $c$  is the concentration of nitrogen in (g nitrogen m<sup>-3</sup>),  $D_N^*$  is in (m<sup>2</sup> min<sup>-1</sup>), and  $a_N$  is the nitrogen activity with the indices  $s$  and  $i$  referring to the subnitride-gas and subnitride-chromium interfaces, respectively. Differentiating Equation (2) and setting  $a_N = p_{N_2}^{1/2}$  gives:

$$D_N^* = \frac{1}{c^2 \cdot 2 \cdot 303} \frac{dk}{d \log p_{N_2}} \quad (3)$$

A simplifying assumption involved in the derivation of Equations (2) and (3) is that the concentration  $c$  is essentially constant and that the unidirectional diffusional flux at a given time is the same in all planes throughout the tarnish layer; this is a reasonable assumption for phases of narrow composition range.

For "Cr<sub>2</sub>N", which has a relatively wide composition range, Schwerdtfeger<sup>1</sup> derived the following modification of Wagner's equation, based on the assumption that the nitrogen concentration profile across the subnitride is linear.

$$k'' = \left( \frac{4c_i + 2c_s}{3(c_i + c_s)^2} \right) \int_{a_{N_i}}^{a_{N_s}} c D_N^* d \ln a_N \quad (4)$$

where  $c_i$  and  $c_s$  are the nitrogen concentrations at the subnitride/gas and subnitride/chromium interfaces, respectively. Differentiating Equation (4) and setting  $a_N = p_{N_2}^{1/2}$  gives

$$D_N^* = \frac{4}{3 \cdot 2 \cdot 303 c_i (c_i + c_s)^2} \left\{ (2c_i + c_s) \frac{dk}{d \log p_{N_2}} - \frac{3c_i + c_s}{c_i + c_s} k - \frac{c_i - c_s}{c_i + c_s} \right\} \quad (5)$$

Schwerdtfeger's<sup>1</sup> data for the concentration of nitrogen in the subnitride  $c_s$  and the composition,  $x$  in Cr<sub>2</sub>N<sub>x</sub>, fit the linear relation

$$c_s = (684x + 92) \cdot 10^3 \quad (6)$$

Equation (5) may be modified using  $dc/dx = 684 \cdot 10^3$  to give

$$D_N^* = \frac{1}{1 \cdot 727 c_i (c_i + c_s)^2} \left\{ (2c_i + c_s) \frac{dk}{d \log p_{N_2}} - \frac{684 \cdot 10^3 c_s}{c_i + c_s} \frac{dx}{d \log p_{N_2}} - \frac{c_i - c_s}{c_i + c_s} \right\} \quad (7)$$

Values of  $c_i$ ,  $c_s$  and  $dx/d \log p_{N_2}$  were calculated from the present authors' composition/pressure data (Ref. 6, Fig. 1).  $k''$  and  $dk/d \log p_{N_2}$  were obtained from Figure 3. The data are

of the curves were calculated using a five-point formula for the first derivative of an experimental function (Lanczos<sup>8</sup>).

If diffusion in chromium subnitride is accomplished essentially by random motion of nitrogen vacancies, the self-diffusivity should be proportional to the ratio of the number of vacant nitrogen sites to the number of occupied nitrogen sites ( $n_N/n_{N_1} = (1-x)/x$ ). Values of  $D_N^*$  calculated using Equation (7)<sup>†</sup> are plotted as a function of  $n_N/n_{N_1}$  in Figures 4 and 5. The proposed linear relationship was not obtained. Instead the curves passed through a minimum which suggests that the intrinsic diffusivity  $D_N$  of nitrogen varies with the composition of the subnitride.

The diffusivity  $D_N$  can be related to the self-diffusivity  $D_N^*$  by the equation

$$D_N^* = 2 D_N \frac{d \ln c}{d \ln p_{N_2}} \quad (8)$$

which may be re-arranged to give

$$D_N^* = \frac{2 D_N}{2.303 c} \frac{dc}{dv} \frac{dv}{d \log p_{N_2}} \quad (9)$$

Values of  $D_N$  calculated using Equation (9) are plotted as a function of composition in Figure 6. The intrinsic diffusivity of nitrogen is shown to depend on composition, increasing towards both the lower and upper limits of the composition range of the subnitride; the minimum shifts to lower nitrogen contents with increasing temperature.

$D_N^*$  was calculated using Equation (9) and constant values for  $D_N$ . The results for the temperatures 1100° and 1250° C are plotted in Figures 4 and 5. The values of  $D_N$  used were the minimum values for the curves in Figure 6 and it is seen that the equilibrium data (Ref. 6, Fig. 1) give a linear relation between  $D_N^*$  and  $n_N/n_{N_1}$  if  $D_N$  is independent of composition; however, the curves do not pass through the origin.

It was not possible to calculate meaningful values of activation energies from the data due to the large variations of  $c_v$  and the dissociation pressure of the subnitride with temperature, and the complex dependence of the diffusivity on composition and temperature.

Schwerdtfeger<sup>1</sup> measured the intrinsic diffusivity of nitrogen in chromium subnitride at 1200° C and concluded that it was essentially independent of composition. The variations in diffusivity values calculated from the kinetic data are large enough to be readily measured experimentally. A study of the diffusivity of nitrogen in chromium subnitride will be undertaken to assess the validity of the calculations of diffusivities in the present work.

## 5. CONCLUSIONS

A new technique with a single specimen has been used successfully to determine the kinetics of the reaction of nitrogen with chromium over a wide range of temperature and nitrogen pressure.

Nitrogen diffusivities in chromium subnitride calculated using Wagner's oxidation theory indicate that the diffusivity varies with composition, passing through a minimum value at intermediate compositions. The composition having the minimum diffusivity varies with temperature.

<sup>†</sup> Equation (7) reduces to Equation (3) on putting  $c_v = c$ , and neglecting the second term in the brackets; this second term was found to be 10% or less of the first term, and putting  $c_v = c$  increased the first term by a corresponding amount, so that values of  $D_N^*$  calculated from Equation (7) agreed with those calculated from Equation (3) to within 1.8%.



TABLE I

Parabolic Rate Constants for the Formation of Chromium Subnitride Layer on Chromium in Nitrogen

$p_{N_2}$ kPa	$k''$ $\text{g}^2 \text{m}^{-1} \text{min}^{-1}$	$p_{N_2}$ kPa	$k''$ $\text{g}^2 \text{m}^{-1} \text{min}^{-1}$	$p_{N_2}$ kPa	$k$ $\text{g}^2 \text{m}^{-1} \text{min}^{-1}$
1000 °C		1050 °C		1100 °C	
0.265	0.95	0.465	2.0	0.400	2.2
0.665	1.46	0.615	2.6	0.665	3.6
1.335	1.76	0.835	3.1	1.335	5.3
2.665	1.94	1.630	3.6	1.705	7.7
5.865	2.45	3.505	4.6	5.415	8.7
13.335	2.80	8.725	5.3	13.335	10.3
26.665	3.13	14.895	5.9	21.335	11.4
		28.475	6.8	66.665	13.0
		58.465	7.5	101.330	14.2
1150 °C		1200 °C		1250 °C	
0.605	1.56	1.145	4.5	2.410	12.3
0.740	3.5	1.165	8.4	3.475	33.9
1.120	7.1	1.970	14.7	5.880	51.9
1.730	10.0	2.915	21.6	10.730	73.5
2.775	13.0	4.440	29.1	20.875	87.6
4.670	16.0	7.010	34.5	46.845	105.3
8.415	19.4	11.550	41.4	89.150	119.7
11.620	21.4	20.420	46.2		
16.485	22.9	39.355	54.3		
36.520	25.9	85.795	61.2		
98.190	30.2				

## REFERENCES

1. Arkharov, V. I., Konev, V. N., and Menshikov, A. Z. *Fiz Metal. i Metalloved* 7, 64 (1959); translated in *Phys. Metals Metallog. (USSR)*, 7, 58 (1959).
2. Hagel, W. C. *Trans. Am. Soc. Metals*, 56, 583 (1963).
3. Seybolt, A. U., and Haman, D. H. *Trans. Met. Soc. AIME*, 230, 1294 (1964).
4. Schwerdtfeger, K. *Trans. Met. Soc. AIME*, 239, 1432 (1967).
5. Mills, T. J. *Less-Common Metals*, 22, 373 (1970).
6. Mills, T. J. *Less-Common Metals*, 26, 223 (1972).
7. Wagner, C. *Atom Movements (A.S.M., Cleveland, 1951)*, p. 153.
8. Lanczos, C. *Applied Analysis (Pitman, London, 1957)*, p. 231.




Fig. 1. Typical examples showing that a parabolic rate law is obeyed in the nitriding of chromium over the temperature range  $1000\text{--}1250^\circ\text{C}$ .




Fig. 2. Curves showing the effect of nitrogen pressure on nitriding kinetics of chromium at 1150°C.




Fig. 3. Parabolic rate constant for the nitriding of chromium as a function of nitrogen pressure at six temperatures.




Fig. 4. Self-diffusivity of nitrogen in chromium subnitride at 1000°, 1050° and 1100°C as a function of composition, —O— calculated from Eq. (7), —●— calculated from Eq. (9) for 1100°C assuming  $D_N$  constant.




Fig. 5. Self-diffusivity of nitrogen in chromium subnitride at 1150°, 1200° and 1250°C as a function of composition, —○— calculated from Eq. (7), ● calculated from Eq. (9) for 1250°C assuming  $D_N$  constant.




Fig. 6. Intrinsic diffusivity of nitrogen in chromium subnitride as a function of composition at six temperatures.



## DISTRIBUTION

Copy No

### AUSTRALIA

#### Department of Defence

##### Central Office

Chief Defence Scientist	1
Deputy Chief Defence Scientist	2
Superintendent, Science and Technology Programs	3
<i>Australian Defence Scientific and Technical Representative (UK)</i>	
Counsellor, Defence Science (USA)	
Joint Intelligence Organisation	4
Defence Library	5
Assistant Secretary, D.L.S.B.	6 21

##### Aeronautical Research Laboratories

Chief Superintendent	22
Library	23
Superintendent Materials Division	24
Divisional File Materials	25
Author: T. Mills	26

##### Materials Research Laboratories

Library	27
---------	----

##### Defence Research Centre, Salisbury

Library	28
---------	----

##### Central Studies Establishment

Information Centre	29
--------------------	----

##### Engineering Development Establishment

Library	30
---------	----

##### RAN Research Laboratory

Library	31
---------	----

##### Defence Regional Office

Library	32
---------	----

##### Army Office

Royal Military College Library	33
US Army Standardisation Group	34

##### Air Force Office

Technical Division Library	35
----------------------------	----

#### Department of Productivity

##### Government Aircraft Factories

Library	36
---------	----

#### Department of Transport

Secretary	37
Library	38

**Statutory, State Authorities and Industry**

Australian Atomic Energy Commission, Director	39
CSIRO, National Measurement Laboratory, Chief	40
CSIRO, Materials Science Division, Director	41
Qantas, Library	42
Trans Australia Airlines, Library	43
Gas and Fuel Corp. of Victoria, Research Director	44
SEC of Vic., Herman Research Laboratory, Librarian	45
SEC of Queensland, Library	46
West. Aust. Govt. Chemical Labs., Library	47
Ampol Petroleum (Vic.) Pty. Ltd., Library	48
Ansett Airlines of Australia, Library	49
Australian Coal Industry Research Labs. Ltd., Director	50
BHP, Melbourne Research Laboratories	51
BP Australia Ltd., Librarian	52
Hawker de Havilland Pty. Ltd., Librarian, Bankstown	53
ICI Australia Ltd., Library	54
Rolls Royce of Australia Pty. Ltd., Mr C. G. A. Bailey	55

**Universities and Colleges**

Adelaide	Barr Smith Library	56
Flinders	Library	57
James Cook	Library	58
Latrobe	Library	59
Melbourne	Engineering Library	60
Monash	Library	61
	Professor I. J. Polmear	62
Newcastle	Library	63
	Professor I. Stewart	64
New England	Library	65
Sydney	Engineering Library	66
N.S.W.	Physical Sciences Library	67
Queensland	Library	68
Tasmania	Engineering Library	69
Western Australia	Library	70
RMIT	Library	71

**CANADA**

Aluminium Laboratories Ltd., Library	72
Canadian Combustion Research Laboratories, Manager	73
Physics and Metallurgy Research Laboratories, Dr A. Williams	74
NRC, National Aeronautical Establishment, Library	75

**Universities and Colleges**

McGill	Library	76
--------	---------	----

**FRANCE**

AGARD, Library	77
Gaz de France, Library	78
ONERA, Library	79
Service de Documentation, Technique de l'Aeronautique	80

**INDIA**

CAARC Co-ordinator Materials	81
Defence Ministry, Aero Development Establishment, Library	82
Fuel Research Institute Director	83
Gas Turbine Research Establishment Director	84
Indian Institute of Science, Library	85
Indian Institute of Technology, Library	86

<b>ISRAEL</b>		
Technion	Israel Institute of Technology, Professor J. Singer	87
<b>JAPAN</b>		
	National Aerospace Laboratory, Library	88
<b>Universities</b>		
Tohoku (Sendai)	Library	89
Tokyo	Institute of Space and Aeroscience	90
<b>NETHERLANDS</b>		
	Central Org. for Applied Science Research TNO, Library	91
	National Aerospace Laboratory (NLR), Library	92
<b>NEW ZEALAND</b>		
	Librarian, Defence Scientific Establishment	93
<b>Universities</b>		
Canterbury	Library	94
<b>SWEDEN</b>		
	Aeronautical Research Institute	96
	Chalmers Institute of Technology, Library	97
	Kungliga Tekniska Hogskolan	98
	SAAB-Scania, Library	99
	Research Institute of the Swedish National Defence	100
<b>UNITED KINGDOM</b>		
	Mr A. R. C. Brown, ADR MAT (MEA)	101
	CAARC, Secretary	102
	Royal Aircraft Establishment:	
	Farnborough, Library	103
	Bedford, Library	104
	Royal Armament Research and Development Establishment	105
	Admiralty Materials Laboratories, Dr R. G. Watson	106
	National Gas Turbine Establishment, Director	107
	British Library, Science Reference Library	108
	British Library, Lending Division	109
	Aircraft Research Association, Library	110
	British Non-Ferrous Metals Res. Assoc.	111
	British Ship Research Association	112
	C. A. Parsons, Gas Turbine Dept., Library	113
	Central Electricity Generating Board	114
	Fulmer Research Institute Ltd., Research Director	115
	Shell Research Laboratory, Director of Fuel Cell Research	116
	Science Museum Library	117
<b>Universities and Colleges</b>		
Bristol	Library, Engineering Department	118
Cambridge	Library, Engineering Department	119
Nottingham	Library	120
Sheffield	Library, Department of Fuel Tech.	121
Southampton	Library	122
Strathclyde	Library	123
Cranfield Institute		
of Technology	Library	124
	Professor Lefebvre	125

**UNITED STATES OF AMERICA**

NASA Scientific and Technical Information Facility	126
The Chemical Abstracts Service	127
Bell Helicopter Textron	128
Metals Abstracts, Editor	129
Calspan Corporation	130
Battelle Memorial Institute, Library	131

**Universities and Colleges**

Polytechnic Institute of New York	Aeronautical Labs. Library	132
California Institute of Technology	Graduate Aeronautical Labs. Library	133

Spares	134 143
--------	---------

DATE  
FILMED  
-87